

	PRESION DE TRABAJO	PRESION DE
RD	KG/CM2	REVENTAMIENTO
		KG/CM2

7.3	17.8	64.7 *
9.0	14.0	56.0
11.0	11.2	45.0
13.5	9.0	36.0
15.5	8.0	32.0
17.0	7.0	28.0
21.0	5.6	22.4
26.0	4.5	18.0
32.5	3.6	14.4
41.0	2.8	11.2



* Nota 1: De acuerdo a la norma ASTM-F714

Nota 2: Algunos valores pueden coincidir por causa de redondeo